



JINHU COLOR POWDER COATING CO.LTD

TEL :+86-25-57909280 | 57909686 FAX :+86-25-57909686
Office@ChinaPowderCoating.com www.ChinaPowderCoating.com

TECHNICAL DATA SHEET

MATT DURABLE POLYESTER POWDER COATING

(FH-MP Series)

INTRODUCTION

FH-MP Series is polyester resins based thermoset powder coating for exterior use. It is formulated to give good flow-out and very matt finish. Its matt finish and outstanding resistance to ultra-violet light and atmospheric aging make it suitable for outdoor use as a decorative and durable coating where very low gloss finished are desired.

GLOSS AND COLOR RANGE

- Gloss levels range : 10 - 30 %
- A wide range colors are available ,certain color is subject to the technical approval .

APPLICATION SCHEDULE

- Applied by electrostatic spraying gun that can provide negative tension of 60-80 kV.
- Curing schedule :10 minutes at 200°C (metal temperature)
- Optimal film thickness : 60 - 80 um

POWDER PROPERTIES

- Specific gravity : 1.25 - 1.75 (depend on colors)
 - Particle size distribution(Laser Particle size analyser) :Less than 5% above 100 um
50 – 65% above 32 um :
- Average particle size : 35- 45um

COATING PROPERTIES

The following are typical properties determined on 0.8 mm gauge degreased galvanised steel

- Film thickness (ISO 2178) : 60 - 80 μm
- Flow out : Good
- Gloss (ISO 2813, 60°) : 10-30 %
- Adhesion (ISO 2409) : GT= 0
- Pencil hardness(ASTM D3363) : H – 2H
- Direct and reverse impact (ASTM D2794) : 50±5kg.cm



JINHU COLOR POWDER COATING CO.LTD

TEL :+86-25-57909280 | 57909686 FAX :+86-25-57909686
Office@ChinaPowderCoating.com www.ChinaPowderCoating.com

- Salt spray Resistance (ASTM B117, 1000hrs)
(Maximum undercutting ,1 mm): No blistering
- Humidity Resistance (ASTM D2247,1000 hrs): No blistering or loss of adhesion
- Chemical Resistance : Film unchanged
(48 hours contact with the coating at ambient temperature)

(Hydrochloric acid 10%,Hydrogen sulphide (saturated),Hydrogen peroxide 40 vol,Ammonium hydroxide 33%,Sodium hydroxide5%,Tartaric acid 5%,Citric acid 5%, Lactic acid 5%, Ethanol, n-Butanol)

SUBSTRATES AND PRE-TREATMENT

In order to obtain optimal anti-corrosion properties, it is recommended to apply a chemical pretreatment prior to powder coating application.

- Ferrous metals(cold rolled steel, cast iron etc.): Iron or zinc phosphatation
- Zinc surfaces(galvanized steel, zinc alloy) : Chromatisation or zinc phosphatation
- Aluminum alloys : Chromatisation

STORAGE

- Under dry conditions ,good ventilation at a temperature not exceeding 25 C,humidity < 60%.
- Storage period recommended should not exceed 6 months,in case exceeding 6 months without affecting their free flowing properties, the powder will still have optimal characteristics.
- Should be protected from excessive heat,humidity,water and contamination with foreign materials such as powder, dust, dirt, etc.
- Any leftover powder should be kept in an appropriate area that is cool and dry. Do not expose to the air too long as the powder properties may deteriorate with the moisture.